





UN38.3 Test Report UN38.3 检测报告

Client 委托方	Nemo Power Tools (Huizhou) Co., Ltd. 尼莫电动工具(惠州)有限公司
Add. of Client 委托方地址	2/F, 4th Industrial Area, Luokeng Village, Xiaotie Zone, Xiaojinkou Town, Huicheng District, Huizhou City, Guangdong Province, China 广东省惠州市惠城区小金口镇小铁区骆坑村第四工业区二层
Name of Sample 样品名称	Lithium Ion Battery 锂离子电池
Model 型号	4S-WHDL
Testing Laboratory 测试机构	Shenzhen TCT Testing Technology Co., Ltd. 深圳市通测检测技术有限公司 2101 & 2201, Zhenchang Factory, Renshan Industrial Zone, Fuhai Subdistrict, Bao'an District, Shenzhen, Guangdong, China 广东省深圳市宝安区福海街道桥头社区稔山工业区振昌胶粘制品厂 2101、2201
Report No. 报告编号	TCT220113B138
Report Versions 版本号	V6.0
Date of Issue 签发日期	2022. 02. 23

Test Conclusion 测试结论:

The test results are qualified. 测试结果为合格。

Carry Wang 135 Tested by 主检人:_

Inspected by 审核人: Amy Ang 家 Seal of TCT 报告单位 (盖章)

Report No. 报告编号: TCT220113B138

Hotline: 400-6611-140 Tel: 86-755-27673339

Fax: 86-755-27673332

Page 1 第 1 页

http://www.tct-lab.com



I、Sample Description 样品描述

Name of Sample 样品名称		Ion Battery 子电池	Model 型号	4S-WI	HDL (
Manufacture 制造商	Shenzhen Tian 深圳市天利合科	lihe Technology Co. ∤技有限公司	, Ltd		
Address 地址	Longteng Comr	munity, Bao'an Distr	ict, Shenzhen	Songbai Road 2852, 工业区 3 栋二层 102、	
Trade Mark 商标		Shape 形状	Prismatic 棱柱形	Size 尺寸 (L×W×T)	(76.0×37.4× 37.4)mm
Nominal Voltage 标称电压	14.8V	Rated Capacity 额定容量	2600mAh 38.48Wh	Limited Charge Voltage 充电限制电压	16.8V
Standard Charge Current 标准充电电流	520mA	Maximum Charge Current 最大充电电流	2600mA	End Charge Current 结束充电电流	26mA
Discharge Cut-off Voltage 放电截止电压	12V	Standard Discharge Current 标准放电电流	520mA	Maximum Discharge Current 最大放电电流	2600mA
Cell Model 电芯型号	MX18650-26 P	Cell Nominal Voltage 电芯标称电压	3.7V	Cell Rated Capacity 电芯额定容量	2600mAh
Cells Numbe 电芯数量	r 4PCS	Start Testing Date 开始测试日期	2019-01-15	Completing Date 完成日期	2019-01-29

Ⅱ、Standard 标准

Recommendations on the Transport of Dangerous Goods, Manual of Test and Criteria (ST/SG/AC.10/11/Rev.6) Sixth revised edition.

联合国《关于危险货物运输的建议书》第六修订版。

Ⅲ、Test Item 测试项目

T.2. 図Thermal test 温度试验

T.3. \(\subseteq \text{Vibration 振动} \)

T.4. ⊠Shock 冲击

Hotline: 400-6611-140

T.7. ⊠Overcharge 过充电

T.8.

Sporced discharge 强制放电

Report No. 报告编号: TCT220113B138

Tel: 86-755-27673339

Page 2 of 18 第2页共 18 页 Fax: 86-755-27673332 http://www.tct-lab.com





Ⅳ、Test Method and Requirement 测试方法和要求

Tests T.1 to T.5 shall be conducted in sequence on the same cell or battery. Tests T.6 and T.8 shall be conducted using not otherwise tested cells. Test T.7 may be conducted using undamaged batteries previously used in tests T.1 to T.5 for purposes of testing on cycled batteries.

用相同的电芯或电池按照顺序进行试验 $T.1 \subseteq T.5$ 。试验 T.6 和 T.8 用没有进行其他试验的电芯。为了测试循环后的电池,试验 T.7 可用试验 $T.1 \subseteq T.5$ 后没有损坏的电池。

Batteries of 1#~8# are full charged after one cycle;

Batteries of 9#~16# are full charged after fifty cycles;

Cells of 17#~21# are 50% charged after one cycle;

Cells of 22#~31# are full discharged after one cycle;

Cells of 32#~41# are full discharged after fifty cycles;

Test environment condition: ambient temperature: 20 ± 5 °C.

电池 1#~8#为一次循环后满电状态;

电池 9#~16#为五十次循环后满电状态;

电芯 17#~21#为一次循环后 50%充电状态;

电芯 22#~31#为一次循环完全放电状态:

电芯 32#~41#为五十次循环完全放电状态;

试验环境条件:环境温度: 20±5℃。

Table 38.3.1: Mass loss limit

表 38.3.1: 质量损失限值

Mass M of cell or battery	Mass loss limit
电芯或电池的质量	质量损失限值
M < 1 g	0.5%
1 g ≤ M ≤75 g	0.2%
M > 75 g	0.1%

In order to quantify the mass loss, the following procedure is provided:

Mass loss (%) = $(M_1 - M_2)/M_1 \times 100$

质量损失的量化值,可用以下公式计算:

Where M₁ is the mass before the test and M₂ is the mass after the test. When mass loss does not exceed the values in Table 38.3.1, it shall be considered as "no mass loss".

式中: M₁ 是试验前的质量, M₂ 是试验后的质量。如果质量损失不超过表 38.3.1 所列的数值,应视为"无质量损失"。

Leakage means the visible escape of electrolyte or other material from a cell or battery or the loss of material (except battery casing, handling devices or labels) from a cell or battery such that the loss of mass exceeds the values in Table 38.3.1.

渗漏是指可以看到的电解液或者其他物质从电芯或电池中漏出,电芯或电池中的物质损失(不包括电池外壳、搬运装置、或标签),质量损失超过表 **38.3.1** 所列的数值。

Venting means the release of excessive internal pressure from a cell or battery in a manner intended by design to preclude rupture or disassembly.

泄气是指按设计方式释放电芯或电池内部过高的压力,防止其破裂或解体。

Disassembly means a vent or rupture where solid matter from any part of a cell or battery penetrates a wire mesh screen (annealed aluminium wire with a diameter of 0.25 mm and grid density of 6 to 7 wires per cm) placed 25 cm away from the cell or battery.



解体是指排气或破裂使电芯或电池任何部分的固体物质穿过放在离电芯或电池 25 cm 处的丝网筛(直径 0.25 mm 的软铝丝,网格密度每厘米 6 至 7 条铝丝)。

Rupture means the mechanical failure of a cell container or battery case induced by an internal or external cause, resulting in exposure or spillage but not ejection of solid materials.

破裂是指内部或外部原因引起的电芯容器或电池外壳机械损坏,造成内置物暴露或溢出,但无固体喷射。

Fire means that flames are emitted from the test cell or battery.

起火是指试验电芯或电池有火焰冒出。

T.1. Altitude simulation 高度模拟

Test procedure 测试程序

Test cells and batteries shall be stored at a pressure of 11.6 kPa or less for at least six hours at ambient temperature (20 ± 5 °C).

试验电芯和电池被放置在压力等于或低于 11.6 kPa 和环境温度(20 ± 5 ℃)下存放至少 6 h。

Requirement 要求

Cells and batteries meet this requirement if there is no leakage, no venting, no disassembly, no rupture and no fire and if the open circuit voltage of each test cell or battery after testing is not less than 90% of its voltage immediately prior to this procedure. The requirement relating to voltage is not applicable to test cells and batteries at fully discharged states.

电芯和电池须无渗漏、无泄气、无解体、无破裂和无起火,并且每个试验电芯和电池在试验后的开路电压不小于其在进行这一试验前电压的 **90%**。有关电压要求不适用于测试完全放电状态的电芯和电池。

T.2. Thermal test 温度试验

Test procedure 测试程序

Test Cells and batteries are to be stored for at least six hours at a test temperature equal to 72 ± 2 °C, followed by storage for at least six hours at a test temperature equal to -40 ± 2 °C. The maximum time interval between test temperature extremes is 30 minutes. This procedure is to be repeated until 10 total cycles are complete, after which all test cells and batteries are to be stored for 24 hours at ambient temperature (20 ± 5 °C). For large cells and batteries the duration of exposure to the test temperature extremes should be at least 12 hours.

试验电芯和电池放置在试验温度等于 72 ± 2 °C 的条件下存放至少 6 h,接着再在试验温度等于 40 ± 2 °C 的条件下存放至少 6 h。两个极端试验温度之间的最大时间间隔为 30 min。此程序重复进行,共完成 10 次,接着将所有试验电池在环境温度(20 ± 5 °C)下存放 24 h。对于大型电芯和电池,暴露于极端试验温度的时间应至少为 12 h。

Requirement 要求

Cells and batteries meet this requirement if there is no leakage, no venting, no disassembly, no rupture and no fire and if the open circuit voltage of each test cell or battery after testing is not less than 90% of its voltage immediately prior to this procedure. The requirement relating to voltage is not applicable to test cells and batteries at fully discharged states.

电芯和电池须无渗漏、无泄气、无解体、无破裂和无起火,并且每个试验电芯和电池在试验后的开路电压不小于其在进行这一试验前电压的 90%。有关电压要求不适用于测试完全放电状态的电芯和电池。

T.3. Vibration 振动

Test procedure 测试程序

Cells and batteries are firmly secured to the platform of the vibration machine without distorting the cells in such a manner as to faithfully transmit the vibration. The vibration shall be a sinusoidal waveform with a logarithmic sweep between 7 Hz and 200 Hz and back to 7 Hz traversed in 15 minutes. This cycle shall be repeated 12 times for a total of 3 hours for each of three mutually perpendicular mounting positions of the cell. One of the directions of vibration must be perpendicular to the terminal face.



The logarithmic frequency sweep shall differ for cells and batteries with a gross mass of not more than 12 kg (cells and small batteries), and for batteries with a gross mass of more than 12 kg (large batteries).

For cells and small batteries: from 7 Hz a peak acceleration of 1 g_n is maintained until 18 Hz is reached. The amplitude is then maintained at 0.8 mm (1.6 mm total excursion) and the frequency increased until a peak acceleration of 8 g_n occurs (approximately 50 Hz). A peak acceleration of 8 g_n is then maintained until the frequency is increased to 200 Hz.

For large batteries: from 7 Hz to a peak acceleration of 1 g_n is maintained until 18 Hz is reached. The amplitude is then maintained at 0.8 mm (1.6 mm total excursion) and the frequency increased until a peak acceleration of 2 g_n occurs (approximately 25 Hz). A peak acceleration of 2 g_n is then maintained until the frequency is increased to 200 Hz.

电芯和电池紧固于振动台台面,但不得造成电池变形,并能准确可靠地传播振动。振动应是正弦波形,对数扫描频率在 7 Hz 和 200 Hz 之间,再回到 7 Hz,1 次循环时间为 15 min。这一振动过程须对三个互相垂直的电池安装方位的每一方向重复进行 12 次,总共为时 3 h。其中一个振动方向必须与端面垂直。

做对数频率扫描对总质量不超过 **12 kg** 的电芯和电池(电芯和小型电池),和对超过 **12 kg** 的电池(大型电池)有所不同。

对电芯和小型电池:从 7 Hz 开始,保持 1 g_n 的最大加速度,直到频率达到 18 Hz。然后将振幅保持在 0.8 mm(总位移 1.6 mm),并增加频率直到峰值加速度达到 8 g_n(频率约为 50 Hz)。将峰值加速度保持在 8 g_n 直到频率增加到 200 Hz。

对于大型电池:从 7 Hz 开始,保持 $1 g_n$ 的最大加速度,直到频率达到 18 Hz。然后将振幅保持在 0.8 mm (总位移 1.6 mm),并增加频率直到峰值加速度达到 $2 g_n$ (频率约为 25 Hz)。将峰值加速度保持在 $2 g_n$ 直到频率增加到 200 Hz。

Requirement 要求

Cells and batteries meet this requirement if there is no leakage, no venting, no disassembly, no rupture and no fire during the test and after the test and if the open circuit voltage of each test cell or battery after testing is not less than 90% of its voltage immediately prior to this procedure. The requirement relating to voltage is not applicable to test cells and batteries at fully discharged states.

电芯和电池须无渗漏、无泄气、无解体、无破裂和无起火,并且每个试验电芯和电池在试验后的开路电压不小于其在进行这一试验前电压的 90%。有关电压要求不适用于测试完全放电状态的电芯和电池。

T.4. Shock 冲击

Test procedure 测试程序

Test cells and batteries shall be secured to the testing machine by means of a rigid mount which will support all mounting surfaces of each test battery.

Each cell shall be subjected to a half-sine shock of peak acceleration of 150 g_n and pulse duration of 6 milliseconds. Alternatively, large cells may be subjected to a half-sine shock of peak acceleration of 50 g_n and pulse duration of 11 milliseconds.

Each battery shall be subjected to a half-sine shock of peak acceleration depending on the mass of the battery. The pulse duration shall be 6 milliseconds for small batteries and 11 milliseconds for large batteries. The formulas below are provided to calculate the appropriate minimum peak accelerations.

Each cell or battery shall be subjected to three shocks in the positive direction and to three shocks in the negative direction in each of three mutually perpendicular mounting positions of the cell or battery for a total of 18 shocks.

试验电芯和电池用刚性支架紧固在试验装置上,支架支撑着每个试验电池的所有安装面。

每个电芯需经受峰值加速度 150 gn 和脉冲持续时间 6 ms 的半正弦波冲击。另外大电芯需要经受峰值加速度 50 gn 和脉冲持续时间 11 ms 的半正弦波冲击。

每个电池接受半正弦波冲击峰值加速度取决于电池的质量,小型电池脉冲持续时间应为 6 ms,大型电池脉冲持续时间为 11 ms 的半正弦波冲击,下面提供的公式来计算适当的最小峰值加速度。

每个电芯或电池需在三个互相垂直的电池安装方位的正方向经受三次冲击,接着在反方向经受三次冲击, 总共经受 18 次冲击。



Requirement 要求

Cells and batteries meet this requirement if there is no leakage, no venting, no disassembly, no rupture and no fire and if the open circuit voltage of each test cell or battery after testing is not less than 90% of its voltage immediately prior to this procedure. The requirement relating to voltage is not applicable to test cells and batteries at fully discharged states.

电芯和电池须无渗漏、无泄气、无解体、无破裂和无起火,并且每个试验电芯和电池在试验后的开路电压不小于其在进行这一试验前电压的 **90%**。有关电压要求不适用于测试完全放电状态的电芯和电池。

Battery	Minimum peak acceleration	Pulse duration
	150 g _n or result of formula	
Small batteries	Acceleration(g _n) = $\sqrt{\left(\frac{100850}{\text{mass}*}\right)}$	6 ms
	whichever is smaller	
Large batteries	50 g _n or result of formula $Acceleration(g_n) = \sqrt{\frac{30000}{mass^*}}$	11 ms
(3)	whichever is smaller	(3)

^{*} Mass is expressed in kilograms.

T.5. External short circuit 外部短路

Test procedure 测试程序

The cell or battery to be tested shall be shall be heated for a period of time necessary to reach a homogeneous stabilized temperature of 57 ± 4 °C, measured on the external case. This period of time depends on the size and design of the cell or battery and should be assessed and documented. If this assessment is not feasible, the exposure time shall be at least 6 hours for small cells and small batteries, and 12 hours for large cells and large batteries. Then the cell or battery at 57 ± 4 °C shall be subjected to one short circuit condition with a total external resistance of less than 0.1 ohm.

This short circuit condition is continued for at least one hour after the cell or battery external case temperature has returned to 57 ± 4 °C, or in the case of the large batteries, has decreased by half of the maximum temperature increase observed during the test and remains below that value.

The short circuit and cooling down phases shall be conducted at least at ambient temperature.

测试的电芯或电池外壳温度达到恒温 57 ± 4 °C 后,再进行外部短路。短路的时间取决于电芯或电池的尺寸和设计,并需被评估和记录。如果这个评估无法进行,那么小电芯和小电池短路时间至少 6 h,大电芯和大电池短路时间至少 12 h。然后电芯或电池在 57 ± 4 °C 环境下经受一个阻值小于 0.1 Ω 的外部电路短路。电芯或电池温度到 57 ± 4 °C 之后,短路时间需持续 1 h,大型电池短路温度下降到最大温升的一半或低于 57 ± 4 °C。

短路和降温阶段至少应在环境温度下进行。

Requirement 要求

Cells and batteries meet this requirement if their external temperature does not exceed 170 °C and there is no disassembly, no rupture and no fire during the test and within six hours after the test.

电芯和电池外壳温度不超过 170 ℃,并且在试验过程中及试验后 6 h 内无解体、无破裂、无起火。

^{*}质量用千克表示





T.6. Impact / Crush 重物冲击/挤压

Test procedure – Impact (applicable to cylindrical cells not less than 18.0 mm in diameter)

测试程序 - 重物冲击(适用于直径大于等于 18.0 mm 的圆柱形电池)

The test sample cell or component cell is to be placed on a flat smooth surface. A 15.8 mm \pm 0.1mm diameter, at least 6 cm long, or the longest dimension of the cell, whichever is greater, Type 316 stainless steel bar is to be placed across the centre of the sample. A 9.1 kg \pm 0.1 kg mass is to be dropped from a height of 61 \pm 2.5 cm at the intersection of the bar and sample in a controlled manner using a near frictionless, vertical sliding track or channel with minimal drag on the falling mass. The vertical track or Channel used to guide the falling mass shall be oriented 90 degrees from the horizontal supporting surface.

The test sample is to be impacted with its longitudinal axis parallel to the flat surface and perpendicular to the longitudinal axis of the 15.8 mm \pm 0.1mm diameter curved surface lying across the centre of the test sample. Each sample is to be subjected to only a single impact.

测试电芯或元件电芯样品放在平坦光滑表面上。一根 316 型不锈钢棒横放在测试样品中心,钢棒直径 15.8 mm ± 0.1 mm, 长度至少 6 cm,或电芯最长尺寸,取二者之长者。将一块 9.1 kg ± 0.1 kg 的重锤从 61 ± 2.5 cm 高度跌落到钢棒和测试样品交叉处,使用一个几乎没有摩擦的,对落体重锤阻力最小的垂直轨道或管道加以控制。垂直轨道或管道用于引导落锤与水平表面成 90° 落下。

受撞击的测试样品,纵轴应与平坦表面平行,并与横放在测试样品中心直径为 15.8 ± 0.1 mm 弯曲表面的纵轴垂直。每一个测试样品只经受一次撞击。

Test procedure – Crush (applicable to prismatic, pouch, coin/button cells and cylindrical cells less than 18.0 mm in diameter)

测试程序 - 挤压(适用于棱形、袋状、硬币/纽扣电芯和圆柱形电芯直径小于 18.0 mm)

A cell or component cell is to be crushed between two flat surfaces. The crushing is to be gradual with a speed of approximately 1.5 cm/s at the first point of contact. The crushing is to be continued until the first of the three options below is reached.

- (a) The applied force reaches 13 kN ± 0.78 kN;
- (b) The voltage of the cell drops by at least 100 mV; or
- (c) The cell is deformed by 50% or more of its original thickness.

Once the maximum pressure has been obtained, the voltage drops by 100 mV or more, or the cell is deformed by at least 50% of its original thickness, the pressure shall be released.

A prismatic or pouch cell shall be crushed by applying the force to the widest side. A button/coin cell shall be crushed by applying the force on its flat surfaces. For cylindrical cells, the crush force shall be applied perpendicular to the longitudinal axis.

Each test cell or component cell is to be subjected to one crush only. The test sample shall be observed for a further 6 h. The test shall be conducted using test cells or component cells that have not previously been subjected to other tests.

将电芯或元件电芯放在两个平面之间挤压,挤压力度逐渐加大,在第一个接触点上的速度大约为 1.5 cm/s。挤压持续进行,直到出现以下三种情况之一:

- (a)施加的力量达到 13 kN ± 0.78 kN:
- (b)电芯的电压下降至少 100 mV; 或
- (c)电芯形变达原始厚度的 50%或更多。
 - 一旦达到最大压力、电压下降 100 mV 或更多,或电芯形变至少达原厚度的 50%,即可解除压力。

棱柱形或袋状电芯须从最宽的面施压。纽扣/硬币形电芯须从平坦表面施压。圆柱形电芯须从与纵轴垂直的方向施压。

每个试验电芯或元件电芯只做一次挤压试验。试验样品须继续观察 6 h。试验须使用之前未做过其他试验的电芯进行。

Requirement 要求

Cells and component cells meet this requirement if their external temperature does not exceed 170 °C and there is no disassembly and no fire during the test and within six hours after this test.

电芯和元件电芯外壳温度不超过 170 ℃,并且在试验过程中及试验后 6 h 内无解体、无起火。





T.7. Overcharge 过充电

Test procedure 测试程序

The charge current shall be twice the manufacturer's recommended maximum continuous charge current. The minimum voltage of the test shall be as follows:

- (a) When the manufacturer's recommended charge voltage is not more than 18 V, the minimum voltage of the test shall be the lesser of two times the maximum charge voltage of the battery or 22 V.
- (b) When the manufacturer's recommended charge voltage is more than 18 V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage.

Tests are to be conducted at ambient temperature. The duration of the test shall be 24 hours.

充电电流为制造商建议的最大持续充电电流的两倍。试验的最小电压如下:

- (a) 制造商建议的充电电压不大于 18 V 时,试验的最小电压应是电池最大充电电压的两倍或 22 V 两者中的较小者。
 - (b) 当制造商建议的充电电压超过 18 V, 试验的最小电压应是最大充电电压的 1.2 倍。试验应在环境温度下进行。进行试验的时间应为 24 h。

Requirement 要求

Rechargeable batteries meet this requirement if there is no disassembly and no fire during the test and within seven days after the test.

可充电电池在试验过程中和试验后7天内无解体、无起火。

T.8. Forced discharge 强制放电

Test procedure 测试程序

Each cell shall be forced discharged at ambient temperature by connecting it in series with a 12 V D.C. power supply at an initial current equal to the maximum discharge current specified by the manufacturer.

The specified discharge current is to be obtained by connecting a resistive load of the appropriate size and rating in series with the test cell. Each cell is forced discharged for a time interval (in hours) equal to its rated capacity divided by the initial test current (in ampere).

每个电芯在环境温度下与12 V 直流电电源串联在起始电流等于制造商规定的最大放电电流的条件下强制放电。

电芯与一个适当大小的电阻负载串联以调节到规定大小的放电电流。每个电芯的放电时间(单位为h)等于电芯的额定容量除以试验初始放电电流(单位A)。

Requirement 要求


Primary or rechargeable cells meet this requirement if there is no disassembly and no fire during the test and within seven days after the test.

不可充电或可充电的电芯在试验过程中和试验后7天内无解体、无起火。

 Report No. 报告编号: TCT220113B138
 Page 8 of 18 第8页共 18 页



V、Test procedure 测试流程







Ⅵ、Main Test Apparatus 主要测试仪器

Serial No. 设备编号	Name of Equipment 设备名称	Model 型号	Calibration Date /Due Date 校准日期/到期日
TC-B01	Low Altitude Simulation Tester	GX-3020-Z	2018. 04. 20
10-601	低压高空模拟试验箱	GA-3020-2	2019. 04. 19
TC-B04	Vertical Shock Test Instrument	SY10-2	2018. 04. 20
10 804	垂直冲击试验台	01102	2019. 04. 19
TC-B05	Vibration test instrument	ES-3-150	2018. 04. 20
10-505	振动试验台	25-5-150	2019. 04. 19
TC-B07	Battery Test System	CTS 20V/10A	2018. 04. 20
10-607	电池测试系统	010 20 V/10A	2019. 04. 19
TC-B11	Crush Test Instrument	BE-6045T	2018. 04. 20
10-011	温控型电池挤压试验机	52 00 101	2019. 04. 19
TC-B13	Battery Short Circuit Tester	GX-6055-B	2018. 04. 20
ТС-Б13	电池短路试验机	GX-0033-B	2019. 04. 19
TC-B14	Electronic Balance	PTT-A+300	2018. 04. 20
10-614	电子天平	F11-A+300	2019. 04. 19
TC-B15	Data Collector	34970A	2018. 04. 20
10-613	数据采集器	34970A	2019. 04. 19
TC-B18	DC POWER	P2TSW 80-27	2018. 04. 20
ТС-ВТ6	直流源	F213W 80-21	2019. 04. 19
TC-B21	Battery Impact Tester	BE-5066	2018. 04. 20
1 O-D2 I	电池冲击试验机	DE-3000	2019. 04. 19
TC-B25	Digital Multimeter	15B	2018. 09. 11
TC-620	数字万用表	100	2019. 09. 10
TC P40	Programmable high & low temperature test chamber	DE TU 450M0 4	2018. 09. 11
TC-B10	可程式高低温试验机	BE-TH-150M8-4	2018. 09. 11

 Report No. 报告编号: TCT220113B138
 Page 10 of 18 第10页共 18 页



Ⅷ、Test Data 测试数据

T.1. Altitude simulation 高度模拟

Test		Pre-tes	t 试验前	After tes	t 试验后		(0)	
sample status 测试样品 状态	No. 编号	Mass 质量 (g)	Voltage 电压 (V)	Mass 质量 (g)	Voltag e 电压 (V)	Mass loss 质量损失 (%)	Change ratio 电压比(%)	Status 结果
Full charged after one cycle 一次循环后满电状态 Full charged after fifty cycles 50 次循环后满电状态	1#	195.052	16.72	195.052	16.72	0.00	100.0	Pass 合格
	2#	194.810	16.72	194.810	16.71	0.00	99.9	Pass 合格
	3#	197.539	16.70	197.539	16.70	0.00	100.0	Pass 合格
	4#	195.151	16.72	195.141	16.72	0.01	100.0	Pass 合格
	9#	194.694	16.71	194.694	16.70	0.00	99.9	Pass 合格
	10#	194.580	16.72	194.580	16.72	0.00	100.0	Pass 合格
	11#	194.110	16.71	194.110	16.71	0.00	100.0	Pass 合格
	12#	194.197	16.72	194.197	16.72	0.00	100.0	Pass 合格
A Company of the Comp								

Notes 注释: Ambient temperature 环境温度: 23.1 °C。

After the test, there is no leakage, no venting, no disassembly, no rupture and no fire. And change ratio is not less than 90 %. 测试后,样品无渗漏、无泄气、无解体、无破裂和无起火。电压比不小于 90 %。

T.2. Thermal test 温度试验

Test	No. 编号	Pre-test 试验前		After test 试验后				
sample status 测试样品 状态		Mass 质量 (g)	Voltage 电压 (V)	Mass 质量 (g)	Voltag e 电压 (V)	Mass loss 质量损失 (%)	Change ratio 电压比(%)	Status 结果
Full charged after one cycle 一次循环后满电状态 Full charged after fifty cycles 50 次循环后满电状态	1#	195.052	16.72	195.040	16.65	0.01	99.6	Pass 合格
	2#	194.810	16.71	194.789	16.60	0.01	99.3	Pass 合格
	3#	197.539	16.70	197.500	16.60	0.02	99.4	Pass 合格
	4#	195.141	16.72	195.102	16.60	0.02	99.3	Pass 合格
	9#	194.694	16.70	194.625	16.59	0.04	99.3	Pass 合格
	10#	194.580	16.72	194.541	16.59	0.02	99.2	Pass 合格
	11#	194.110	16.71	194.089	16.60	0.01	99.3	Pass 合格
	12#	194.197	16.72	194.174	16.60	0.01	99.3	Pass 合格

Notes 注释: Ambient temperature 环境温度: 23.3 °C。

After the test, there is no leakage, no venting, no disassembly, no rupture and no fire. And change ratio is not less than 90 %. 测试后,样品无渗漏、无泄气、无解体、无破裂和无起火。电压比不小于 90 %。



T.3. Vibration 振动

Test	No. 编号	Pre-test 试验前		After test 试验后				
sample status 测试样品 状态		Mass 质量 (g)	Voltage 电压 (V)	Mass 质量 (g)	Voltag e 电压 (V)	Mass loss 质量损失 (%)	Change ratio 电压比(%)	Status 结果
Full charged	1#	195.040	16.65	195.040	16.64	0.00	99.9	Pass 合格
after one cycle	2#	194.789	16.60	194.778	16.60	0.01	100.0	Pass 合格
一次循环后	3#	197.500	16.60	197.500	16.60	0.00	100.0	Pass 合格
满电状态	4#	195.102	16.60	195.102	16.59	0.00	99.9	Pass 合格
Full charged	9#	194.625	16.59	194.625	16.59	0.00	100.0	Pass 合格
after fifty cycles 50 次循环后	10#	194.541	16.59	194.541	16.58	0.00	99.9	Pass 合格
	11#	194.089	16.60	194.089	16.60	0.00	100.0	Pass 合格
满电状态	12#	194.174	16.60	194.174	16.60	0.00	100.0	Pass 合格

Notes 注释: Ambient temperature 环境温度: 23.0 ℃。

After the test, there is no leakage, no venting, no disassembly, no rupture and no fire. And change ratio is not less than 90 %. 测试后,样品无渗漏、无泄气、无解体、无破裂和无起火。电压比不小于 90 %。

T.4. Shock 冲击

	Pre-test 试验前		After tes	After test 试验后			
No. 编号	Mass 质量 (g)	Voltage 电压 (V)	Mass 质量 (g)	Voltag e 电压 (V)	Mass loss 质量损失 (%)	Change ratio 电压比(%)	Status 结果
1#	195.040	16.64	195.040	16.63	0.00	99.9	Pass 合格
2#	194.778	16.60	194.778	16.60	0.00	100.0	Pass 合格
3#	197.500	16.60	197.500	16.60	0.00	100.0	Pass 合格
4#	195.102	16.59	195.102	16.58	0.00	99.9	Pass 合格
9#	194.625	16.59	194.612	16.59	0.01	100.0	Pass 合格
10#	194.541	16.58	194.541	16.58	0.00	100.0	Pass 合格
11#	194.089	16.60	194.074	16.60	0.01	100.0	Pass 合格
12#	194.174	16.60	194.174	16.60	0.00	100.0	Pass 合格
	编号 1# 2# 3# 4# 9# 10# 11#	No. 編号 Mass 质量 (g) 1# 195.040 2# 194.778 3# 197.500 4# 195.102 9# 194.625 10# 194.541 11# 194.089	No. 編号 Mass	No. 编号 Mass 质量 (g) Voltage 电压 (V) Mass 质量 (g) 1# 195.040 16.64 195.040 2# 194.778 16.60 194.778 3# 197.500 16.60 197.500 4# 195.102 16.59 195.102 9# 194.625 16.59 194.612 10# 194.541 16.58 194.541 11# 194.089 16.60 194.074	No. 编号 Mass 质量 (g) Voltage 电压 (V) Mass 质量 (V) Voltage 电压 (V) 质量 电压 (V) 1# 195.040 16.64 195.040 16.63 2# 194.778 16.60 194.778 16.60 3# 197.500 16.60 197.500 16.60 4# 195.102 16.59 195.102 16.58 9# 194.625 16.59 194.612 16.59 10# 194.541 16.58 194.541 16.58 11# 194.089 16.60 194.074 16.60	No. 编号 Mass 质量 (g) Voltage 电压 (V) Mass 质量 (V) Mass loss 质量损失 (V) 1# 195.040 16.64 195.040 16.63 0.00 2# 194.778 16.60 194.778 16.60 0.00 3# 197.500 16.60 197.500 16.60 0.00 4# 195.102 16.59 195.102 16.58 0.00 9# 194.625 16.59 194.612 16.59 0.01 10# 194.541 16.58 194.541 16.58 0.00 11# 194.089 16.60 194.074 16.60 0.01	No. 编号 Mass 质量 (g) Voltage 电压 (V) Mass 质量 电压 (V) Voltage 电压 (V) Mass 质量损失 电压 (%) Change ratio 电压比(%) 1# 195.040 16.64 195.040 16.63 0.00 99.9 2# 194.778 16.60 194.778 16.60 0.00 100.0 3# 197.500 16.60 197.500 16.60 0.00 100.0 4# 195.102 16.59 195.102 16.58 0.00 99.9 9# 194.625 16.59 194.612 16.59 0.01 100.0 10# 194.541 16.58 194.541 16.58 0.00 100.0 11# 194.089 16.60 194.074 16.60 0.01 100.0

Notes 注释: Ambient temperature 环境温度: 23.7 °C。

After the test, there is no leakage, no venting, no disassembly, no rupture and no fire. And change ratio is not less than 90 %. 测试后,样品无渗漏、无泄气、无解体、无破裂和无起火。电压比不小于 90 %。





T.5. External short circuit 外部短路

Test sample status 测试样品状态	No. 编号	Maximum external temperature (°C) 表面最高温度(°C)	Status 结果
	1#	57.5	Pass 合格
Full charged after one cycle	2#	57.3	Pass 合格
一次循环后满电状态	3#	57.4	Pass 合格
	4#	57.3	Pass 合格
	9#	57.7	Pass 合格
Full charged after fifty cycles 50 次循环后满电状态	10#	57.2	Pass 合格
	11#	57.6	Pass 合格
	12#	57.3	Pass 合格

Notes 注释: Ambient temperature 环境温度: 23.8 °C。

Test sample external temperature does not exceed 170 °C and there is no disassembly, no rupture and no fire during the test and within six hours after the test.

测试样品表面温度不超过 170°C,测试中与测试后 6 h 内无解体、无破裂、无起火。

T.6. Impact 重物冲击

Test sample status 测试样品状态	No. 编号	Maximum external temperature (°C) 表面最高温度(°C)	Status 结果
(c)	17#	78.6	Pass 合格
50% charged after	18#	80.2	Pass 合格
one cycle 一次循环后 50%充电 状态	19#	74.6	Pass 合格
	20#	80.2	Pass 合格
	21#	81.2	Pass 合格

Notes 注释: Ambient temperature 环境温度: 23.8 °C。

Test sample external temperature does not exceed 170 °C and there is no disassembly, no rupture and no fire during the test and within six hours after the test.

测试样品表面温度不超过 170°C,测试中与测试后 6 h 内无解体、无破裂、无起火。

T.7. Overcharge 过充电

	Test sample status 测试样品状态	No. 编号	Status 结果
		5#	Pass 合格
	Full charged after one cycle	6#	Pass 合格
	一次循环后满电状态	7#	Pass 合格
		8#	Pass 合格

Report No. 报告编号: TCT220113B138 Page 13 of 18 第13页共 18 页



	13#	Pass 合格
Full charged after fifty cycles	14#	Pass 合格
50 次循环后满电状态	15#	Pass 合格
	16#	Pass 合格

Notes 注释: Ambient temperature 环境温度: 23.3 °C。

There is no disassembly and no fire during the test and within seven days after the test.

样品在测试中和测试后7天内无解体、无起火。

T.8. Forced discharge 强制放电

Test sample status 测试样品状态	No. 编号	Status 结果
Full discharged after one cycle 一次循环完全放电状态	22#	Pass 合格
	23#	Pass 合格
	24#	Pass 合格
	25#	Pass 合格
	26#	Pass 合格
	27#	Pass 合格
	28#	Pass 合格
	29#	Pass 合格
	30#	Pass 合格
	31#	Pass 合格
Full discharged after fifty cycles 50 个循环完全放电状态	32#	Pass 合格
	33#	Pass 合格
	34#	Pass 合格
	35#	Pass 合格
	36#	Pass 合格
	37#	Pass 合格
	38#	Pass 合格
	39#	Pass 合格
	40#	Pass 合格
	41#	Pass 合格

Notes 注释: Ambient temperature 环境温度: 23.2 °C。


There is no disassembly and no fire during the test and within seven days after the test.

样品在测试中和测试后7天内无解体、无起火。


Report No. 报告编号: TCT220113B138 Page 14 of 18 第14页共 18 页



Ⅷ、Picture of the sample 样品图片



Picture 1. Battery view 图片 1. 电池视图



Picture 2. Battery view 图片 2. 电池视图

Report No. 报告编号: TCT220113B138 Page 15 of 18 第15页共 18页

Hotline: 400-6611-140 Tel: 86-755-27673339 Fax: 86-755-27673332 http://www.tct-lab.com





Picture 3. Cell view 图片 3. 电芯视图




Picture 4. Cell view 图片 4. 电芯视图


Report No. 报告编号: TCT220113B138 Page 16 of 18 第16页共 18页

Hotline: 400-6611-140 Tel: 86-755-27673339 Fax: 86-755-27673332 http://www.tct-lab.com





Picture 5. Protection board view 图片 5. 保护板视图



Picture 6. Protection board view 图片 6. 保护板视图

******End of Report 报告结束*****

Report No. 报告编号: TCT220113B138 Page 17 of 18 第17页共 18 页



Important Notice

注意事项

1. The test report is invalid without the official stamp of TCT.

本报告书无 TCT 盖章无效。

2. Nobody is allowed to photocopy or partly photocopy this test report without written permission of TCT.

未经 TCT 书面同意,不得复制或部分地复制本报告书。

- 3. The test report is invalid without the signatures of Ratifier, Reviewer and Testing engineer. 本报告书无批准人、审核人、及主检人签名无效。
- 4. The report is invalid when anything of following happens illegal transfer, reproduce, embezzlement, imposture, modification or tampering in any media form.
 私自转让、复制、盗用、冒用、涂改、或以任何媒体形式篡改的报告书无效。
- 5. Objections to the test report must be submitted to TCT within 15 days. 对报告书若有异议,应于收到报告之日起 15 天内向本公司提出。
- 6. The test report is valid for the tested samples only.

本报告仅对本次测试样品有效。

- 7. The Chinese contents in this report are only for reference. 本报告中的中文内容仅供参考。
- 8. This report belongs to quote for the record, the reference test report TCT190117B022. 此报告为报备案件,参考测试报告 TCT190117B022。



Shenzhen TCT Testing Technology Co., Ltd. 深圳市通测检测技术有限公司 2101 & 2201, Zhenchang Factory, Renshan Industrial Zone, Fuhai Subdistrict, Bao'an District, Shenzhen, Guangdong, China

广东省深圳市宝安区福海街道桥头社区稔山工业区振昌胶粘制品厂 2101、2201

Search Number 查询编号: TCT220113B138 Search System 查询系统: http://www.tct-lab.com